

Lewatit® NM 60 is a highly regenerated mixed bed ion exchange resin consisting of a 1:1 chemically equivalent mixture of a type 1, strong base anion exchange resin and a strong acid cation exchange resin.

Lewatit® NM 60 is especially suited for the applications mentioned below:

- » in mixed bed units for polishing after primary demineralization systems
- » in electronic industries
- » in small industrial plants (e.g. refilling of starter batteries or coolant circuits)
- » for the removal of radioactive waste
- » in demineralization systems.

The special properties of this product can only be fully utilized if the technology and process used correspond to the current state-of-the-art. Further advice in this matter can be obtained from Lanxess, Business Unit Liquid Purification Technologies.

This document contains important information and must be read in its entirety.





Common Description

| Delivery form | H⁺/OH⁻ |
|------------------|---------------------|
| Functional group | Quaternary ammonium |
| | Typ1 /sulfonic acid |
| Matrix | Styrenic |
| Structure | Gel |
| Appearance | Dark brown / Yellow |
| | translucent |

Specified Data

| Uniformity coefficient | | max. | 1.8 |
|------------------------------------|--------------------------|--------------|-----------|
| Effective size | d10 | mm | 0.40-0.65 |
| Mixed bed test (column capacity) | 0,02 MOhm*cm endpoint | min. eq/L | 0.55 |
| Mixed bed test (polishing quality) | NaCl exhaustion | min. MOhm*cm | 16 |

This document contains important information and must be read in its entirety.





Typical Physical and Chemical Properties

| Bulk density for shipment (+/- 5%) | g/L | 690 |
|------------------------------------|------------------|-----------|
| Density | approx. g/mL | 1.1 |
| Water retention (delivery form) | approx. weight % | 50-60 |
| Volume change (during exhaustion) | max. approx. % | -15 |
| Stability pH range | | 0-14 |
| Storage temperature range | °C | -20 - +40 |

Operation

| Operating temperature | | max. °C | 60 |
|---|-------------------|-----------------|------|
| Operating pH range | during exhaustion | | 0-14 |
| Bed depth for single column | | min. mm | 600 |
| Specific pressure loss kPa*h/m² (15°C) | | kPa*h/m² (15°C) | 1.5 |
| Max. pressure loss during operation | | kPa | 200 |
| Specific flow rate | | max. BV/h | 50 |

This document contains important information and must be read in its entirety.





Additional Information & Regulations

Safety precautions

Strong oxidants, e.g. nitric acid, can cause violent reactions if they come into contact with ion exchange resins

Toxicity

The safety data sheet must be observed. It contains additional data on product description, transport, storage, handling, safety and ecology.

Disposal

In the European Community Ion exchange resins have to be disposed, according to the European waste nomenclature which can be accessed on the internet-site of the European Union.

Storage conditions

It is recommended to store ion exchange resins at temperatures above the freezing point of water under roof in dry conditions without exposure to direct sunlight. If resin should become frozen, it should not be mechanically handled and left to thaw out gradually at ambient temperature. It must be completely thawed before handling or use. No attempt should be made to accelerate the thawing process.

Storage time

The recommended storage time for this product is explained in the technical document "Technical guidelines on the storage of Lewatit® ion exchange resins" available for download on our website. Please use the following link for more information: https://lanxess.com/en/products-and-brands/brands/lewatit/literature

Packaging

The experience has shown that the packaging stability for reliable resin containment is limited to 24 months under the storage conditions described above. It is therefore recommended to use the product within this time frame; otherwise the packaging condition should be checked regularly.

This information and our technical advice – whether verbal, in writing or by way of trials – are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

LANXESS Deutschland GmbH Liquid Purification Technologies Kennedyplatz 1 50569 Koeln Germany

This document contains important information and must be read in its entirety.

